IMPORTANT! Before using this product, read all precautions on SDS. Before applying GRIP-COAT™ read all application instructions on Product Data Sheet. Product Data Sheets & SDS are available at www.garonproducts.com or by calling 1-800-631-5380.

DESCRIPTION: GRIP-COAT™ RESURFACER with sand is a durable, efficient surface coating especially designed for all-weather tennis courts, blacktop areas and other sport and recreational pavement areas. GRIP-COAT™ RESURFACER has 100% Acrylic resins emulsions which provides the ultimate in protection and beauty for asphaltic surfaces. GRIP-COAT™ RESURFACER is designed for onsite mixing with water.

SURFACE PREPARATION: Surface should be clean. Remove all loose sand, dust, vegetation and other foreign material. New asphalt must cure for a minimum of four weeks before application

VOC: This material contains less than 250 grams of volatile organic compounds per liter.

MIXING: Mix GRIP-COAT™ RESURFACER well. Hand mixing is not recommended. Use of a mixing blade at slow speed, high torque drill (not to exceed 650 RPM), is acceptable. Stir thoroughly prior to application.

STORAGE: STORE AT ROOM TEMPERATURE, KEEP FROM FREEZING.

KEEP OUT OF REACH OF CHILDREN

HMIS CODE: H:2; F:0; P:0

GARON PRODUCTS. INC. PO BOX 1924, WALL, NJ 07719 1-800-631-5380 www.garonproducts.com

GARON

SPORTS SURFACE RESURFACING AND PATCHING COMPOUND

GRIP-COAT[™] RESURFACER

MIXING: Coating GRIP-COAT™ RESURFACER-5 gallons. WATER - 2 gallons MIXING: Patching Use less water and add coarse angular sand

SET TIME: Allow each coat of GRIP-COAT™ RESURFACER to dry thoroughly before

applying successive coats.

PACKAGING: 5-Gallon Pail

YIELD/COVERAGE: UNDILUTED - Approximately .11 -.13 gallons per square yard, per coat. Will vary according to surface texture and porosity

MADE IN U.S.A.

Read carefully other cautions on side panel. For Industrial Use Only

NOTE: GRIP-COAT™ RESURFACER can be modifier for patching and filling low spots by adding more sand and less water. A coarse angular sand should be used for patching mixes.

APPLICATION: Apply GRIP-COAT™ RESURFACER with a soft rubber squeegee. Scrape all rough spots and ridges before applying successive coats. Allow GRIP-COAT™ RESURFACER to completely dry before applying additional coats.

CLEAN UP: Wash tools in water before GRIP-COAT™ RESURFACER dries.

CAUTION: Do not take internally. If swallowed, call a physician immediately. In case of contact with eyes, flush immediately with water for 15 minutes and call a physician. When not in use, keep container tightly closed and upright to prevent leakage. Do not store in direct sunlight or above 100 degrees F. In case of spillage, absorb and dispose of in accordance with Federal, State, Local regulations. KEEP FROM FREEZING

LIMITATONS: Do not apply to frozen surfaces or if temperature will fall below 50°F within 24 hours. Minimum ambient and surface temperatures at 50°F and rising at time of application. Do not apply when rain is eminent or forecast. Use above grade only. Not for structural applications. The user is responsible for proper application

Garon Products are sold with the understanding that the buyer will test them actual use and determine for himself their adaptability to his intended use. However, since such is beyond our control, we do not guarantee the results to be obtained in the customer's processes. The information contained in this brief is advisory only, and the use of the materials and methods are solely at the risk of the user. These recommendations and suggestions for the use of our materials are in accordance with Garon standards. There are no other warranties by Garon of any nature whatsoever, expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product, and under no circumstances, either expressed or implied, will GARON PRODUCTS, INC. be liable for damages in excess of the purchase price of this product. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by the officers of manufacturer and seller.