

DANGER! Causes skin irritation. Causes serious eye damage. May cause an allergic skin reaction. May cause respiratory irritation. May cause cancer.

PRECAUTIONARY STATEMENT! Before using this product, read all precautions on SDS. Before applying HEAT PATCH™, read all application instructions on Product Data Sheet. Product Data Sheets & SDS are available at www.garonproducts.com or by calling 1-800-631-5380. Do not eat, drink or smoke when using this product. Wash hands thoroughly after handling. Contaminated work clothing must not be allowed out of the workplace. Wear protective gloves/protective clothing/eye protection/face protection. Use only outdoors or in a well-ventilated area. Do not breathe dust. Store locked up. Store in a well-ventilated place. Keep container tightly closed. Store locked up. Dispose of in accordance with local, state, and federal regulations.

FIRST AID: If Swallowed: Immediately call a poison center/doctor. Rinse mouth. If in Eyes: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Immediately call a poison center/doctor. If on Skin: Wash with plenty of water. Take off contaminated clothing and wash it before reuse. If skin irritation or rash occurs get medical advice/attention. If exposed or concerned get medical advice/attention. If Inhaled: Remove person to fresh air and keep comfortable for breathing. Call a poison center/doctor if you feel unwell.

KEEP OUT OF REACH OF CHILDREN

HMIS CODE: H:3; F:1; P:0



GARON PRODUCTS, INC
PO BOX 1924, WALL, NJ 07719
1-800-631-5380
www.garonproducts.com

GARON

EXTREME HEAT CONCRETE REPAIR PATCH

HEAT-PATCH™

MIXING: 5.5 QUARTS WATER TO 50 POUNDS OF POWDER

SET TIME: Initial Cure: 3-4 hours. **Final Cure:** 5-6 hour

YIELD/COVERAGE: 5 gallons fills approximately 1/2 cubic foot

PACKAGING: 5-Gallon Pail

MADE IN U.S.A.

Read carefully other cautions on side panel.
For Industrial Use Only

SURFACE PREPARATION: All dirt, oil, dust, foreign contaminants, peeling coating and laitance must be removed from surface prior to use. Make a vertical cut with a masonry saw around the area to be repaired. Remove material within the area. Refer to Garon's Concrete Surface Preparation Guideline for additional information.

MIXING: For smaller installations, hand mixing or drill mixing with a low speed, high torque drill (not to exceed 650 RPM) is acceptable. Add HEAT PATCH™, to the water and mix to a smooth, lump-free consistency. Do not mix for more than 2 minutes, and install immediately after mixing. Mix enough material to permit continuous placement before any part of the HEAT PATCH™ has set, but do not mix more material than can be placed in 8 to 10 minutes. Do not re-temper once material has started to set, or the mix will be spoiled. If too much water is added promptly mix in more HEAT PATCH™, to restore the proper consistency. After mixing, discharge material immediately and flush mixer with clean water to clean up.

LIMITATIONS: Do not apply to frozen surfaces or if temperature will fall below 40°F within 24 hours. Minimum ambient and surface temperatures at 45°F and rising at time of application. Use above grade only. Not for structural applications. The user is responsible for proper application

Garon Products are sold with the understanding that the buyer will test them actual use and determine for himself their adaptability to his intended use. However, since such is beyond our control, we do not guarantee the results to be obtained in the customer's processes. The information contained in this brief is advisory only, and the use of the materials and methods are solely at the risk of the user. These recommendations and suggestions for the use of our materials are in accordance with Garon standards. There are no other warranties by Garon of any nature whatsoever, expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product, and under no circumstances, either expressed or implied, will GARON PRODUCTS, INC. be liable for damages in excess of the purchase price of this product. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by the officers of manufacturer and seller.