

DANGER! Causes skin irritation. Causes serious eye damage. May cause an allergic skin reaction. May cause respiratory irritation. May cause cancer.

PRECAUTIONARY STATEMENT! Before using this product, read all precautions on SDS. Before applying TIGERCRETE SP™, read all application instructions on Product Data Sheet. Product Data Sheets & SDS are available at www.garonproducts.com or by calling 1-800-631-5380. Avoid breathing dust. Wash thoroughly after handling. Use only outdoors or in a well-ventilated area. Contaminated work clothing should not be allowed out of the workplace. Wear protective gloves/protective clothing/eye protection/face protection. Store in a well-ventilated place. Keep container tightly closed. Store locked up. Dispose of in accordance with local, state, and federal regulations.

FIRST AID: If exposed or concerned: Get medical advice/attention. If inhaled: If breathing is difficult, remove person to fresh air and keep comfortable for breathing. Call a poison center/doctor if you feel unwell. If on skin: Wash with plenty of water. Take off contaminated clothing and wash before reuse. If skin irritation or rash occurs: Get medical advice/attention. If in eyes: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Immediately call a poison center/doctor.

KEEP OUT OF REACH OF CHILDREN

HMIS CODE: H:2; F:0; P:0



GARON PRODUCTS, INC
PO BOX 1924, WALL, NJ 07719
1-800-631-5380
www.garonproducts.com

GARON

High-Performance, Flowable, Trowelable, Non-Shrink Grout

TIGERCRETE™ SP

MIXING: 4.5 QUARTS WATER TO 50 POUNDS OF POWDER

SET TIME: Initial Cure: 10 Minutes. Final Cure: 20 Minutes. Allow to cure for 24 hours before applying weight or stress.

YIELD/COVERAGE: 5 gallons fills approximately 1/2 cubic foot

PACKAGING: 5-Gallon Pail

MADE IN U.S.A.

Read carefully other cautions on side panel.
For Industrial Use Only

SURFACE PREPARATION: : All surfaces must be structurally sound, clean and free of dust, dirt, oils, paints and all other contaminants that will prevent proper bond. Make certain all loose material is removed. Acid based cleaning solutions must be neutralized. Where applicable, provide air relief openings to avoid entrapment of air. All metal components that will be in contact with TIGERCRETE™ SP must be rust free and free of paints, oil sand release agents. All concrete that will contact TIGERCRETE™ SP must be thoroughly saturated with water, but allow no standing water to remain. Any wood forms should be surface saturated before placing TIGERCRETE™ SP. Forms should be lined or coated with re-bond breaker for easy removal, seams, caulked to prevent leakage.

MIXING: TIGERCRETE™ SP requires only the addition of water. No other additives should be used. Add water to a suitable mixing vessel. A mortar type mixer with rotating, rubber edged blades is recommended for larger applications and those at a lower flow. For smaller installations, hand mixing or drill mixing with a low speed, high torque drill (not to exceed 650 RPM) is acceptable. Add material to water and mix to a smooth, lump-free consistency. Do not mix for more than 2 minutes, and install immediately after mixing. Mix enough material to permit continuous placement before any part of the TIGERCRETE™ SP has set, but do not mix more material than can be placed in 5 minutes. A good consistency for most concrete repairs requires 4-1/2 quarts of water per 50 pounds of TIGERCRETE™ SP. For a flowable grout, up to 6 quarts of water per 50 pounds may be used. A flowable consistency is recommended for anchoring bolts, posts or rails.

LIMITATIONS: Do not apply to frozen surfaces or if temperature will fall below 40°F within 24 hours. Minimum ambient and surface temperatures at 45°F and rising at time of application. Use above grade only. Not for structural applications. The user is responsible for proper application

Garon Products are sold with the understanding that the buyer will test them actual use and determine for himself their adaptability to his intended use. However, since such is beyond our control, we do not guarantee the results to be obtained in the customer's processes. The information contained in this brief is advisory only, and the use of the materials and methods are solely at the risk of the user. These recommendations and suggestions for the use of our materials are in accordance with Garon standards. There are no other warranties by Garon of any nature whatsoever, expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product, and under no circumstances, either expressed or implied, will GARON PRODUCTS, INC. be liable for damages in excess of the purchase price of this product. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by the officers of manufacturer and seller.